

TEST REPORT

Report No: SZ151120019EN

Report Date: 2015/11/12

Applicant Zhongshan Kingho Chemical Industrial Co.,LTD
Address No.82, Zhongheng Road, Henglan Town, Zhongshan City, Guangdong, China

The following sample(s) and sample information was/were submitted and identified by/on the behalf of the client

Sample Name Two component polyurethane adhesive
 Sample Description Sample is mixed according to the proportion
 DJ-9263A/AW9263=20:4
 Style No. DJ-9263A/AW9263
 Sample Received Date 2015.11.06
 Testing Period 2015.11.06-2015.11.12


As specified by client, to test the submitted sample(s) as below.

TEST REQUIRMENT(S)
TEST ITEM(S)
1. Test for Compliance with U.S.F.D.A.C.F.R.21. Part 175.300
CONCLUSION
1. The submitted sample 001 was found to comply with the respective requirement(s) for the test item(s) as specified in US FDA 21 CFR Part 175.300.

Note: "EN" denotes English report

***** For Further Details, Please Refer To the Following Page(s) *****

Tested by  _____
 Approved by  _____
 loey Fan
 Vice General Manager

Checked by  _____
 Date 2015.11.12

TEST REPORT

Report No: SZ151120019EN

Report Date: 2015/11/12

TEST RESULT**1. TEST FOR COMPLIANCE WITH US FDA 21 CFR PART 175.300.**

TEST ITEM	RESULTS (mg/in ²)	Limit (mg/in ²)
	001	
Total extractives in distilled water (121°F for 24 hours)	0.13	0.5*
8% ethanol extractives (121°F for 24 hours)	0.19	0.5*
Heptane extractives (70°F for 0.5 hours)	0.15	0.5*

Note:

- "mg/in²" denotes milligram per square inch
- "°F" denotes degree Fahrenheit
- "*" - For single use, volume < 1 gallon


TEST REPORT

Report No: SZ151120019EN

Report Date: 2015/11/12

TESTED SAMPLE/PART DESCRIPTION

Sample	Tested Material Description
001	Transparent plastic piece

Photo(s) of the sample(s)

*** End of Report ***

The test report is effective only with both signature and specialized stamp. The result(s) shown in this report refer only to the sample(s) tested. Without written approval of IMPAQ, this report can't be reproduced except in full.