



171500113641



(2017)鲁质监验字007号



中国认可
国际互认
检测
TESTING
CNAS L1184

检 验 报 告

TEST REPORT

NO. QTC-715002683

产 品 名 称 包装用聚乙烯吹塑薄膜

规 格 型 号 980×0.095 (mm)

生 产 企 业 名 称 烟台广源塑料有限公司

检 验 类 别 生产许可证检验



青 岛 市 产 品 质 量 监 督 检 验 研 究 院
Qingdao Product Quality Supervision and Testing Research Center




青岛市产品质量监督检验研究院

检验报告

NO. QTC-715002683

共 2 页 第 1 页

产品名称	包装用聚乙烯吹塑薄膜			商 标	/
规格型号	980×0.095 (mm)			生产日期 或批号	2019-05-10
生产企业名称	烟台广源塑料有限公司			联系电话	15865622025
抽样日期	2019-05-15	抽样人员	张建春、刘丞	样品到达 日期	2019/05/16
抽样数量	3卷×2.5m ² ×2	检查封样 人员	孙春鹏	样品编号	71502683
抽样基数	6卷×173.5kg/卷	抽样单编号	食塑包发(鲁) 第20190280号	检验日期	2019-05-17~ 2019-05-30
样品状态	包装用聚乙烯吹塑薄膜, 无印刷, 样品封样完好, 符合检验要求				
任务来源	山东省质量技术监督局				
检验类别	生产许可证检验				
检验项目	拉伸强度等11项				
检验依据	GB/T 4456—2008、《食品用塑料包装、容器、工具等制品生产许可审查细则》				
检验结论	<p>按GB/T 4456—2008和《食品用塑料包装、容器、工具等制品生产许可审查细则》, 本次发证检验合格</p> <div style="text-align: right;">  <p>(检验报告专用章) (1)</p> </div> <p style="text-align: right;">签发日期: 2019/06/1</p>				
备注	材质: PE-LD/PE-LLD薄膜 材质为乙烯均聚物 无添加剂 无印刷 接触食品的种类 为多种, 预期使用条件为冷冻 使用前在容器内再加热 备样量及封存地点: 3卷×2.5m ² , 封存于发证检验机构				
批准:	王晓滨		审核:	陈东	
			主检:	孙春鹏	

青岛市产品质量监督检验研究院检验报告附页

No. QTC-715002683

共 2 页 第 2 页

序号	检验项目	技术要求	检验结果	单项判定
1	拉伸强度			合格
1.1	纵向	≥11MPa	23MPa	
1.2	横向	≥11MPa	29MPa	
2	断裂伸长率			合格
2.1	纵向	≥150%	1096%	
2.2	横向	≥150%	1416%	
3	冲击强度	不破裂样品数≥8个	10个样品均不破裂	合格
4	高锰酸钾消耗量	≤10mg/L	1.95mg/L	合格
5	蒸发残渣(4%乙酸)	≤30mg/L	4.00mg/L	合格
6	蒸发残渣(65%乙醇)	≤30mg/L	6.50mg/L	合格
7	蒸发残渣(正己烷)	≤60mg/L	11.0mg/L	合格
8	重金属	≤1mg/L	<1mg/L	合格
9	脱色试验(乙醇)	阴性	无色、阴性	合格
10	脱色试验(冷餐油)	阴性	无色、阴性	合格
11	脱色试验(浸泡液)			合格
11.1	水浸泡液	阴性	无色、阴性	
11.2	4%乙酸浸泡液	阴性	无色、阴性	
11.3	65%乙醇浸泡液	阴性	无色、阴性	
11.4	正己烷浸泡液	阴性	无色、阴性	

试验说明：

- 试验室环境温度：22.9℃~23.5℃ 相对湿度50.7%~51.5%
- 拉伸强度、断裂伸长率：按 GB/T 1040.3—2006 检验
- 冲击强度：按 GB/T 9639.1—2008 检验
- 高锰酸钾消耗量、蒸发残渣、重金属、脱色试验：按 GB/T 5009.60—2003 检验

以 下 空 白



注意事项

- 1、报告无“检验检测专用章”无效。
- 2、检验报告未经本院/中心书面批准不得复制（全文复制除外），经特许复制的报告需重新加盖“检验检测专用章”，否则无效。
- 3、报告无主检、审核、批准人签章无效。
- 4、报告涂改无效。
- 5、考虑到您的利益，如果对委托检验报告结果有异议，请在收到报告之日起十五日内向检验单位提出。
- 6、送样委托检验，检验结果仅对来样负责。未经本院/中心同意，委托人不得擅自使用检验结果进行不当宣传。

- 1、The report is invalid without Inspection report special stamp.
- 2、Do not copy the report unless specially permitted. The copy must be sealed with inspection report special stamp ,otherwise it would be invalid.
- 3、The report would be invalid if there is no signature of the major inspector, verifier or authorizer.
- 4、The report would be invalid if altered.
- 5、Any question with the Commissioned inspection report should be submitted to the inspection unit within 15 days from receiving the report .After the specified date any request would be refused.
- 6、Sample offered inspection results refer only to the sample(s) tested. Do not use the results for improper propaganda.

地址：青岛市崂山区深圳路173号
邮编：266061
电话：0532-8891-8000
传真：0532-8891-8100
网址：www.qtc.org.cn
E-mail: qdzjs@qtc.org.cn

Add: No.173 Shenzhen Road Qingdao China
P. C. : 266061
Tel: 0532-8891-8000
Fax: 0532-8891-8100
Website: www.qtc.org.cn
E-mail: qdzjs@qtc.org.cn



微信公众号二维码